

IG464-U

Melt Index 10.0

Density 0.964

Features

- Superior stiffness allows for part thinwalling and improved stack strength
- Low viscosity for exceptional processability, shorter cycle times, and energy savings
- Exceptional physical properties provide impact resistance for demanding applications
- Low warpage for improved part quality and reliability

Additives

- Antioxidant
- UV Stabilizer

Applications

- Crates
- Pallets
- Totes
- Pails

Properties	ASTM (1)	Typical Values (2)	
		Compression Molded	Injection Molded
Melt Index (3)	D 1238	10.0 g/10 min	
Density	D 792	0.964 g/cm ³	
Tensile Strength @ Yield (50 mm/min)	D 638	33 MPa (4 785 psi)	27 MPa (3 915 psi)
Tensile Strength @ Break (50 mm/min)		15 MPa (2 175 psi)	20 MPa (2 900 psi)
Elongation @ Yield (50 mm/min)	D 638	7 %	8 %
Elongation @ Break (50 mm/min)		100 %	1 250 %
Flexural Modulus @ 1%	D 790	1 700 MPa (246 565 psi)	1 300 MPa (188 550 psi)
Vicat Softening Point	D 1525	131 °C (268 °F)	
Hardness, Shore D	D 2240	68	

(1) Properties designated have been determined using methods which are in accordance with or substantially in accordance with the specified testing standards.

(2) Typical Values represent average laboratory values and are intended as guides only, not as specifications.

(3) Condition 190°C/2.16 kg.

IG464-U - HDPE

SCLAIR

Availability

SCLAIR polyethylene resins are available in bulk hopper cars, hopper trucks, boxes, sea bulk containers or bags. The product type and batch number are clearly marked on each container. Contact the NOVA Chemicals sales office nearest you for availability in your area.

Storage/Handling

IG464-U should be stored in a clean, dry place at ambient temperatures. Prolonged or improper storage can result in deterioration of product properties. Care should be taken when handling and transferring product to prevent foreign matter contamination. The NOVA Chemicals material safety data sheet (MSDS) contains important safety information and should be reviewed before using the product.

Processing Conditions

Comprehensive assistance with processing conditions and technology is available from NOVA Chemicals Technical Service at (403) 291-8444.

Food Packaging Status

United States: IG464-U complies with the specifications contained in the U.S. Food and Drug Administration (FDA) regulation 21 CFR 177.1520 for olefin polymers, para. (c) 3.2a, and may thus be used in the United States as an article or component of an article intended for use in contact with food. IG464-U is subject to the specific limitation that it may contact food only at temperatures of 212°F and below (21 CFR 176.170(c) Table 2, conditions of use B-H).

Other Countries: For regulatory compliance information for other countries, please contact your nearest NOVA Chemicals office.

Environmental

NOVA Chemicals' polyethylene resins are biologically and chemically inert, but improper disposal may present an ingestion hazard to wildlife. Where recycling of NOVA Chemicals' polyethylene resins is not possible, disposal to landfill or incineration in accordance with all applicable government laws and regulations is recommended. Please contact NOVA Chemicals Technical Service for further information on recycling and disposal of NOVA Chemicals resins.



HDPE is the SPI resin code developed for high density polyethylene to identify material type for sorting and recycling purposes.

www.novachemicals.com

U.S. Operating Center
NOVA Chemicals Inc.
 1550 Coraopolis Heights Road
 Moon Township, PA 15108
 United States of America

Phone 412.490.4000
 Toll Free 800.222.7213
 Fax 412.494.4861

European Operating Center
NOVA Chemicals (International) S.A.

Avenue de la Gare 14
 1700 Fribourg
 Switzerland

Phone 41.26.426.57.57
 Fax 41.26.426.57.70

Technical Center

NOVA Chemicals Technical Center
 3620 – 32 Street N.E.
 Calgary, Alberta
 Canada T1Y 6G7

Phone 403.291.8444
 Fax 403.291.0493

Headquarters

NOVA Chemicals Corporation
 1000 Seventh Avenue S.W.
 P.O. Box 2518, Station M
 Calgary, Alberta
 Canada T2P 5C6

Phone 403.750.3600
 Fax 403.269.7410

 **NOVA Chemicals**® is a registered trademark of NOVA Brands Ltd; authorized use.

SCLAIR® is a registered trademark of NOVA Chemicals Corporation in Canada and of NOVA Chemicals International S.A. elsewhere; authorized use.

The above information is provided in good faith without warranty, representation, inducement or license of any kind. No freedom from infringement of any patent owned by NOVA Chemicals or others is to be inferred. NOVA Chemicals is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, NOVA CHEMICALS MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN OR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user.